



HOBAS®

Fiberglass Reinforced Polymer Mortar (FRPM) Pipe – Non-Pressure (Sewer) Service

Specifications

Engineered to Endure™

If in Doubt, Seek Advice from Hobas Pipe USA, Inc. • 800.856.7473

GENERAL

Machine made fiberglass pipe for gravity flow service

References

1. ASTM D3262 – Standard Specification for "Fiberglass" (Glass-Fiber-Reinforced Thermosetting-Resin) Sewer and Industrial Pipe.
2. ASTM D2412 – Standard Test Method for External Loading Characteristics of Plastic Pipe by Parallel Plate Loading.
3. ASTM D4161 – Standard Specification for Fiberglass Pipe Joints Using Flexible Elastomeric Seals.
4. ASTM D3681 – Standard Test Method for Chemical Resistance of "Fiberglass" Pipe in a Deflected Condition.

Specifications

1. The specifications contained herein govern, unless otherwise agreed upon between the purchaser and supplier.

PRODUCTS

Materials

1. **Resin Systems** The manufacturer shall use only polyester resin systems with a proven history of performance in this particular application. The historical data shall have been acquired from a composite material of similar construction and composition as the proposed product.
2. **Glass Reinforcements** The reinforcing glass fibers used to manufacture the components shall be of highest quality commercial grade glass filaments with binder and sizing compatible with impregnating resins.
3. **Silica Sand** Sand shall be minimum 98% silica with a maximum moisture content of 0.2%.
4. **Additives** Resin additives, such as curing agents, pigments, dyes, fillers, thixotropic agents, etc., when used, shall not detrimentally effect the performance of the pipe.
5. **Elastomeric Gaskets** Gaskets shall meet ASTM F477 and be supplied by qualified gasket manufacturers and be suitable for the service intended.

Manufacture and Construction

1. **Pipes** Manufacture pipe utilizing a machine-made process to result in a dense, nonporous, corrosion-resistant, consistent composite structure. The interior surface of the pipes exposed to sewer flow shall provide crack resistance and abrasion resistance. Pipes shall be manufactured in accordance with ASTM D3262.

(continued)

PRODUCTS

Manufacture and Construction (continued)

2. **Joints** Unless otherwise specified, the pipe shall be field connected with fiberglass sleeve couplings that utilize elastomeric sealing gaskets as the sole means to maintain joint watertightness. The joints must meet the performance requirements of ASTM D4161. Tie-ins, when needed, may utilize gasket-sealed mechanical couplings.
3. **Fittings** Flanges, elbows, reducers, tees, wyes, laterals and other fittings shall be capable of withstanding all operating conditions when installed. They may be contact molded or manufactured from mitered sections of pipe joined by glassfiber reinforced overlays. Properly protected standard ductile iron, fusion-bonded epoxy-coated steel and stainless steel fittings may also be used.
4. **Acceptable Manufacturer** Hobas Pipe USA, Inc.

Dimensions

1. **Diameters** The actual outside diameter (18" to 48") of the pipes shall be in accordance with ASTM D 3262. For other diameters, OD's shall be per manufacturer's literature.
2. **Lengths** Per manufacturer.
3. **Wall Thickness** The minimum wall thickness shall be the stated design thickness.
4. **End Squareness** Pipe ends shall be square to the pipe axis with a maximum tolerance of 1/8"

Testing

1. **Pipes** Pipes shall be manufactured and tested in accordance with ASTM D3262.
2. **Joints** Coupling joints shall meet the requirements of ASTM D4161.
3. **Stiffness** Minimum pipe stiffness when tested in accordance with ASTM D2412 shall normally be 36 psi.

Customer Inspection

1. The Owner or other designated representative shall be entitled to inspect pipes or witness the pipe manufacturing.
2. **Manufacturer's Notification to Customer:** Should the Owner request to see specific pipes during any phase of the manufacturing process, the manufacturer must provide the Owner with adequate advance notice of when and where the production of those pipes will take place.

Packaging, Handling, Shipping

1. Packaging, handling, and shipping shall be done in accordance with the manufacturer's instructions.

EXECUTION

Installation

- 1. Installation** The installation of pipe and fittings shall be in accordance with the project plans and specifications and the manufacturer's requirements.
- 2. Pipe Handling** Use textile slings, other suitable materials or a forklift. Use of chains or cables is not recommended.
- 3. Jointing**
 - a. Clean ends of pipe and coupling components.
 - b. Apply joint lubricant to pipe ends and the elastomeric seals of coupling. Use only lubricants approved by the pipe manufacturer.
 - c. Use suitable equipment and end protection to push or pull the pipes together.
 - d. Do not exceed forces recommended by the manufacturer for coupling pipe.
 - e. Join pipes in straight alignment then deflect to required angle. Do not allow the deflection angle to exceed the deflection permitted by the manufacturer.
- 4. Field Tests**
 - a. Infiltration / Exfiltration Test – Maximum allowable leakage shall be per local specification requirements.
 - b. Low Pressure Air Test – Each reach may be tested with air pressure (max 5 psi). The system passes the test if the pressure drop due to leakage through the pipe or pipe joints is less than or equal to the specified amount over the prescribed time period.
 - c. Individual Joint Testing – For pipes large enough to enter, individual joints may be pressure tested with a portable tester to 5 psi max. with air or water in lieu of line infiltration, exfiltration or air testing.
 - d. Deflection – Maximum allowable long-term deflection is normally 5% of the initial diameter.